



## PRODUCT APPLICATION

Stir paint thoroughly

### Application methods:

- brush
- roller
- conventional sprayer

**Thinner:** item number 8002. Amount of thinner 0-5% by volume. If more thinner is added the desired effect may not be achieved.

When spraying – it is recommended to use higher pressure and thicker paint so that a more visible hammer effect is achieved. A test sample on the surface is recommended.

## APPLICATION

### Surface

- ALMADECOR HAMMER EFFECT does not require a primer, however, in order to enhance the anti-corrosion protection ALMAKOR-TIX may be used as a primer.
- ALMAKOR-TIX coating or ALMAKOR C free from corrosion, grease, dust. The surface must be dry.
- Clean the surface with water and allow to dry. Repair any damages on the coat

### Painting and curing conditions

- minimal surface temperature should be above the dew point (omitting condensation)
- air temperature above 5°C
- good ventilation

**SHELF LIFE:** 9 months from the production date in original unsealed container.

**WARNING!** This product is designed for professional use in the given industry. Detailed information regarding product safety can be found in the MSDS.